

■ POLYMER ADDITIVES

## JADEWIN UV326


### CHEMICAL COMPONENT

COMPONENT 2-(5-Chloro-2H-benzotriazol-2-yl)-6-(1,1-dimethylethyl)-4-methylphenol

CAS 3896-11-5

Molecular C17H18ClN3O

M.W 316



### SPECIFICATION AND PHYSICAL PROPERTIES

TEST	UNIT	SPECIFICATION
APPEARANCE		LIGHT YELLOWISH POWDER
ASSAY	%	99.00MIN
VOLATILES	%	0.50MAX
ASH	%	0.10MAX
MELTING POINT	°C	137.0-142.0
TRANSMITTANCE		
460nm	%	93.00MIN
500nm	%	96.00MIN
TGA236°C5%	250°C10%	287°C50%

### FEATURE AND APPLICATION

\* JADEWINUV326 is a strong absorber of ultraviolet radiation in the 300~400 nm region and has a high degree of photostability - photochemical energy absorbed in the ultraviolet region is dissipated as thermal energy.

\* Differs from JADEWINUV234 principally in a greater absorption of longer wavelengths, better compatibility with polyolefins, lower volatility, and suppressed ionization of the phenolic grouping.



- \* Is less affected by alkalinity, is less likely to discolor with metals, and has less effect on metal driers and metal catalysts due to the higher dissociation constant of JADEWINUV 326 (approximately 13 as compared with 11.7 for JADEWINUV234- in 80% aqueous dioxane)
- \* Is recommended for use at levels of 0.2~1.0% in PP, PE, Polybutylene, Polyesters, and Coatings.
- \* Can be used in combination with phenolic & phosphite antioxidants, and HALS to optimize performance in outdoor use.
- \* For additional information please consult the Material safety Data Sheet.

### **PACKING**

20KGCarton Box      25Kg Carton Box

### **STORAGE**

Keep container tightly closed and dry and storage in cool place

### **CHEMICAL INVENTORIES**

Australia - AICS  
Canada - DSL  
EU - EINECS  
China - IECSC  
Japan - ENCS  
Korea - ECL  
USA - TSCA  
Philippines - PICCS