



## ■ POLYMER ADDITIVES

# JADEWIN 3808PP5

### SPECIFICATION AND PHYSICAL PROPERTIES

TEST	UNIT	SPECIFICATION
APPEARANCE		WHITE OR LIGHT YELLOW GRANULES
ADDITIVE CONCENTRATION	%	48.0-52.0
CARRIER		PP
DENSITY	g/cm <sup>3</sup>	0.90-0.94
ASH	%	0.1MAX
VOLATILES	%	0.5MAX
PROCESS TEMPERATURE	°C	120.0-270.0

### FEATURE AND APPLICATION

- \*Excellent compatibility with polyolefins with no observed blooming.
- \*Exceptional surface stabilization used alone or in a combination with UV absorbers.
- \*Effective cost/performance.
- \*Low color contribution and volatility.
- \*Superior performance than traditional formula of JADEWIN 944 and 770.
- \*Polyolefins
- \*Polypropylene
- \*TPO

### PACKING

20KG CARTON/PAPER BARREL

### STORAGE

Keep container tightly closed and dry and storage in cool place

### CHEMICAL INVENTORIES

Australia - AICS  
Canada - DSL  
China - IECSC  
Japan - ENCS  
New Zealand - NZIoC



JADEWIN

杰得盈

Korea - ECL

USA - TSCA

Philippines - PICCS

**QINGDAO JADE NEW MATERIAL  
TECHNOLOGY CO.,LTD**

**青岛杰得佳新材料科技有限公司**